



Dajulong No.12

复合商用卷材地板

DajuLong[®]
大巨龙弹性地板

Dajulong No.12

Dimension: 2.0mm x 2m x 20m




JL12-01



JL12-02



JL12-03



JL12-05




JL12-17




JL12-07

Dajulong No.12


规格: 2.0mm x 2m x 20m




JL12-04



JL12-18




JL12-06



JL12-11




JL12-08




JL12-09

Dajulong No.12


Dimension: 2.0mm x 2m x 20m



JL12-10




JL12-12



JL12-13



JL12-14




JL12-15



JL12-16

Dajulong No.12

规格: 2.0mm x 2m x 20m




JL12-31



JL12-32



JL12-33



JL12-34

Dajulong No.12

复合商用卷材地板



Description 规格	Standard 标准	Result 结果
Total thickness 总厚度	EN 428	2.0 mm
Wear layer thickness 耐磨层	EN 429	0.35 mm
Width 宽度	EN 426	2 m
Length of sheet 卷长	EN 426	20 m

Classification 类别

Fire rating 防火等级	GB 8624-2012	B1
Toxic testing 有害物质检测	GB 18586-2001	Good 合格
Electrical resistance 抗电阻性	EN 1081	$> 10^{9-10}$
Slip resistance dry 防干滑性	EN 13893	≥ 0.3
Slip resistance wet 防湿滑性	DIN 51130	R9

Performances 性能

Castor chair test 轮压测试	EN 425	No damage 合格
Colour fastness 颜色稳定性	EN ISO 105- B02	≥ 6
Chemical products resistance 抗化学性	EN 423	Good 好
Dimensional stability 尺寸稳定性	EN 434	$\leq 0.40\%$
Curl resultant to heat 加热翘曲	EN 434	≤ 1 mm
Sound reduction 消音率	EN ISO 717/2	Approx. 4 dB
Residual indentation 残余凹陷度	EN 433	Approx. 0.04mm 约等于0.04mm
Anti-bacterial and fungicidal 抗菌防霉性能		Good 好
VOC 挥发物排放量		< 10
Surface treatment 表面处理		PUR

Intertek抗菌检测报告



FloorScore环保检测报告



SGS防火检测报告

